

## Product Specifications & Properties

# Mearlite® Ultra Bright UPFMT0000

Product Number UPFMT0000



### Specifications

**Description:** A pearly or nearly metallic paste containing Bismuth Oxychloride, a UV absorber and having a characteristic odor.

### Certifiable Specifications:

**BiOCI** 33 - 37%

**Non-Volatiles: (3 hours at 75°)** 70 – 84%

### Typical Properties

Typical Composition:	By Weight	CAS No.
BiOCI (CI 77163)	33 - 37%	7787-59-9
Triacetin	20 - 26%	102-76-1
Resins (dry)	11- 17%	N/A
Xylene	6 - 12%	1330-20-7
n-Butyl Acetate	7 - 11%	123-86-4
UV absorber	5 - 10%	N/A
Toluene	1 - 3%	108-88-3
IPOH	0.5 - 1.5	67-63-0

**Density:** 12.5 lbs/gal., 1.4 Kg/L

**Flash Point:** 84°F Setaflash Closed cup.

**Uses:** This formulation is suitable for use in unsaturated polyester resin formulations.

NOTES: FOR INDUSTRIAL USE ONLY.

**BASF Corporation**  
100 Campus Drive  
Florham Park, NJ 07932  
Tel: +1-800-962-7831  
Tel: +1-973-245-7399  
Fax: +1-800-975-3123  
Fax: +1-864-332-5080  
[www.basf.com/pigments](http://www.basf.com/pigments)

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

All trademarks are the property of BASF AG, BASF Corporation, or BASF Catalysts LLC.